

TEST REPORT SR 0645/22

Client: Cofratec Indústria Têxtil Ltda.

Address: 6430, Edgar Máximo Zambotto Highway, Franco da Rocha - SP - Brazil.

1 - Sample description: One (01) sample of blue coloured textile material.
Client identification: "1781 04/0354 – Corante Disperso: 4301/4303/4302".

2 - Sample description: One (01) sample of orange coloured textile material.
Client identification: "2295 16/1157 – Corante Disperso: 4265/4272/4247".

3 - Sample description: One (01) sample of white coloured textile material.
Client identification: "2292 23/0844 – Corante Disperso: 7014/4277".



Application: 60422

Date of entry: 01/25/2022

Date of the test: 01/28 until 02/16/2022 and 03/03 until 03/07/2022.

TESTS AND RESULTS

Determination of certain aromatic amines derived from azo colorants with and without extraction (BS EN ISO 14362-1/17)

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum: 20 ppm	PASS

Amines analyzed: Azo dyes can release by cleavage of their azo group, one or more of the amines listed: 2,6-Dimethylaniline, 2-Methylaniline, 4-Chloroaniline, 2-Methoxy-5-Methylaniline, 2,4,5-Trimethylaniline, 4-Chloro-2-Methylaniline, 2,4-Diaminotoluene, 2,4-Diaminoanisole, 2-Naphthylamine, 2-Methyl-5-Nitroaniline, 4-Aminobiphenyl, 4-Aminoazobenzene, 4,4'-Oxydianiline, 4,4'-Diaminobiphenyl, 4,4'-Diaminodiphenylmethane, 4'-Amino-2,3'-Dimethylazobenzene, 4,4'-Methylene-bis(2-methylaniline), 3,3'-Dimethylbenzidine (o-Tolidine), 4,4'-Thiodianiline, 3,3'-Dichlorobenzidine, o-Dianisidine, 4,4'-Methylene bis(2-chloroaniline), o-Anisidine, 2,4-Dimethylaniline.

Arylamine Salts extraction (BS EN ISO 14362-1/17)

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum: 20 ppm	PASS

Salts analyzed: 4-chloro-o-toluidinium chloride, 2-Naphthylammoniumacetate, 2,4,5-trimethylaniline hydrochloride, 4-methoxy-m-phenylene diammonium sulphate; 2,4-diaminoanisole sulphate

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

TEST REPORT SR 0645/22

Textile – Determination of formaldehyde (ISO 14184-1/11)

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	All except packaging: max. 16 ppm	PASS

Determination of Bisphenol (BPA, BPS, BPF, BPAF) (US EPA 3550C: 2007 & US EPA 8321B: 2007)¹

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum: 1 ppm	PASS

Determination of disperse dyes (DIN 54231:2005)¹

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Disperse Blue 1; Disperse Blue 106; Disperse Blue 124; Disperse Orange 3; Disperse Orange 11; Disperse Orange 37/76/59; Disperse Red 1; Disperse Yellow 3; Acid Red 26; Basic Red 9; Basic Violet 14; Direct Black 38; Direct Blue 6; Direct Blue 35: maximum 15 ppm each Others: maximum 50 ppm each	PASS

Determination of organotin compounds (ISO/TS 16179:2012)

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	DBT, DOT, MBT, TCyHT, TMT: 1 ppm each TPhT: 0.5 ppm TBT: 0.1 ppm	PASS

Nonylphenol (NP), Octylphenol (OP), Nonylphenol Ethoxylates (NPEO/OPEO) (EN ISO 18254-1:2016)¹

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Sum of NP and OP: Maximum: 100 ppm Sum of NPEO and OPEO:	PASS

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

TEST REPORT SR 0645/22

Maximum: 100 ppm

Determination of Quinoline (DIN 54231/05)¹

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum: 50 ppm	PASS

Determination of metal content

Part 1: Determination of metals using microwave digestion (BS EN 16711-1:2015)

Analysis performed by ICP-OES

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	Cd = < LQM	Maximum: 40 ppm	PASS
	Pb = < LQM	Maximum: 90 ppm	PASS
	As = <LQM	Maximum: 10 ppm	PASS
	Hg = <LQM	Maximum: 0.5 ppm	PASS

Determination of Benzene and Toluene Chloride (DIN EN 17137:19)¹

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum 1 ppm	PASS

pH Value (ISO 3071/20)

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	7.3	4.0 – 7.5	PASS

Determination of polycyclic aromatic hydrocarbons (PAHs) (ISO 16190/13)

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Total: 10 ppm	PASS

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

TEST REPORT SR 0645/22

Determination of metal content

Part 2: Determination of metals extracted by acidic artificial perspiration solution (BS EN 16711-2:2015)

Analysis performed by ICP-OES

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	Antimony (Sb):	< LQM	Maximum 30 ppm
	Arsenic (As):	< LQM	Maximum 0.1 ppm
	Barium (Ba):	< LQM	Maximum 1000 ppm
	Cadmium (Cd):	< LQM	Maximum 40 ppm
	Chromium (Cr):	< LQM	Maximum 2 ppm
	Lead (Pb):	< LQM	Maximum 0.2 ppm
	Mercury (Hg):	< LQM	Maximum 0.02 ppm
	Selenium (Se):	< LQM	Maximum 500 ppm
	Cobalt (Co):	< LQM	Maximum 1 ppm
	Copper (Cu):	< LQM	Maximum 25 ppm
	Nickel (Ni):	< LQM	Maximum 1 ppm
	Tin (Sn):	< LQM	-
			PASS

Determination of Vinyl Chloride Monomer (EN ISO 6401:2008)¹

Sample	Results (ppm)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum 1 ppm	PASS

Determination of phthalate content (CPSC-CH-C 1001-09.3/2018)*

Sample	Results (%)	Orientation (Manual Veja 2021)	Evaluation
1 + 2 + 3	< LQM	Maximum: 500 ppm each Total: 1000 ppm	PASS

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

TEST REPORT SR 0645/22

Method Quantification Limit – LQM		
- Organotin: 0.2 ppm		
n-butyltin (MBT)	Monooctyltin (MOT)	Trimethyltin (TMT)
tributyltin (TBT)	Di-n-octyltin (DOT)	Tricyclohexyltin (TCyHT)
Dibutyltin (DBT)	Triphenyltin (TPhT)	Trioctyltin (TOT)
Tetrabutyltin (TeBT)	Tripropyltin (TPT)	
- Formaldehyde (Textile): 16 ppm		
- Azo Dyes: 5 ppm per amine		
- Arylamine salts: 5 ppm each		
-PAHs (ppm): 0.5 ppm		
Naphthalene	Benzo[e]pyrene	
Acenaphthylene	Benzo[j]fluoranthene	
Acenaphthene	Chrysene	
Fluorene	Benzo[b]fluoranthene	
Phenanthrene	Benzo[k]fluoranthene	
Anthracene	Benzo[a]pyrene	
Fluoranthene	Indeno[1,2,3-cd]pyrene	
Pyrene	Dibenzo[a,h]anthracene	
Benzo[a]anthracene	Benzo[g,h,i]perylene	
- Quinoline: 10 ppm		
- Alkyl Phenol (ppm):	NP/ OP: 10 ppm	OPEO/ NPEO: 50 ppm
- Bisphenols: 1 ppm		
Bisphenol A (BPA)	Bisphenol-S (BPS)	
Bisphenol-F (BPF)	Bisphenol-AF (BPAF)	
- Soluble Metals BS EN 16711-2:		
Antimony (Sb): 10.0 ppm	Cadmium (Cd): 0.1 ppm	Mercury (Hg): 0.02 ppm
Arsenic (As): 0.1 ppm	Chromium (Cr): 2.0 ppm	Selenium (Se): 10.0 ppm
Barium (Ba): 2.5 ppm	Lead (Pb): 0.2 ppm	Tin (Sn): 10.0 ppm
Cobalt (Co): 1 ppm	Copper (Cu): 2.5 ppm	Nickel (Ni): 1 ppm
- BS EN 16711-1 (Total):		
Lead (Pb): 10.0 ppm	Cadmium (Cd): 10.0 ppm	
Arsenic (As): 10.0 ppm	Mercury (Hg): 0.5 ppm	
- Vinyl Chloride Monomer: 0.2 ppm		
- Benzene and Toluene Chloride: 0.1 ppm		
2,6-Dichlorotoluene	2,3,6-Trichlorotoluene	1,4-Dichlorobenzene
Chlorobenzene	2,4,5-Trichlorotoluene	1,2,3-Trichlorobenzene
2-Chlorotoluene	α,α,α-trichlorotoluene	1,2,4-Trichlorobenzene
3-Chlorotoluene	2,3,4,5-tetrachlorotoluene	1,3,5-Trichlorobenzene
4-Chlorotoluene	2,3,4,6-tetrachlorotoluene	1,2,3,4-Tetrachlorobenzene
α-chlorotoluene	2,3,5,6-tetrachlorotoluene	1,2,3,5-Tetrachlorobenzene
2,3-Dichlorotoluene	α,α,α,4-tetrachlorotoluene	1,2,4,5-Tetrachlorobenzene
2,4-Dichlorotoluene	pentachlorotoluene	Pentachlorobenzene
2,5-Dichlorotoluene	1,2-Dichlorobenzene	Hexachlorobenzene
3,4-Dichlorotoluene	1,3-Dichlorobenzene	

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

TEST REPORT SR 0645/22

Method Quantification Limit – LQM

- Disperse dyestuffs (carcinogenic): 15 ppm

Acid Red 26	Basic Green 4	Disperse Blue 1
Basic Red 9	C.I. Direct Red28	Disperse Blue 3
Basic Violet 14	C.I. Direct Black 38	Disperse Blue 7
Direct Blue 6	Disperse Yellow 49	Disperse Blue 26
Disperse Orange 11	Disperse Orange 1	Disperse Blue 35A and 35B
Direct Brown 95	Disperse Orange 3	Disperse Blue 102
Disperse Red 151	Disperse Orange 37/76/59	Disperse Blue 106
C.I. Basic Violet 3	Disperse Orange 149	Disperse Blue 124
Disperse Red 1	Disperse Yellow 23	Basic Green 4
Disperse Red 11	Disperse Yellow 7	C.I. Solvent Blue 4
Disperse Red 17	Disperse Yellow 56	C.I. Basic Blue26
Solvent Yellow 2	Disperse Yellow 39	Disperse Yellow 9
Disperse Yellow 3	Disperse Yellow 1	

4,4'-bis (dimethylamino)-4''-(methylamino)trityl alcohol

- Phthalates: 0.015 %

Dimethyl phthalate (DMP)	Di-n-hexyl phthalate (DNHP)	Methyl butyl phthalate (MBP)
Di-(2-ethyl-hexyl) phthalate (DEHP)	Butyl benzyl phthalate (BBP)	Di-n-pentyl phthalate (DPP)
Diisobutyl phthalate (DIBP)	Diisodecyl phthalate (DIDP)	Diisooctyl phthalate (DIOP)
Dibutyl phthalate (DBP)	Diethyl phthalate (DEP)	Bis(2-methoxyethyl) phthalate (BMEP)
Diisooheptyl phthalate (DIHP)	Diisononyl phthalate (DINP)	Dipropyl phthalate (DPrP)
Dicyclohexyl phthalate (DCHP)	Di-n-octyl phthalate (DNOP)	Diisopentyl phthalate (DIPP)
N-pentyl-isopentyl phthalate (PiPP)		
1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear		
1,2-benzenedicarboxylic acid, dipentylester, branched and linear		
1,2-benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters (DHNUP)		
1,2-benzenecarboxylic acid, di-C6-10-alkyl esters; 1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with ≥ 0.3% of dihexyl phthalate (EC No. 201-559-5)		

¹This test has been outsourced:

Enterprise: Centre Testing International Group Co., Ltd.

Address: Liuxian 3rd Road, Xin'an Street, Bao'an District, Shenzhen, P.R. China.

Document: A2220074830121

Date: 03/03 until 03/07/2022.

Considerations:

ppm (parts per million) = mg/kg

Sampling was carried by client.

At the customer's request, the samples were grouped. In case of a positive result, IBTeC recommends testing each separate sample.

With the exception of the outsourced tests, the remaining tests were performed in the laboratory permanent facilities.

With no further information for the time being, we now issue the present report.

This report integrates the sheet of signatures attached.

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

Phone +55 51 3553.1000
www.ibtec.org.br
laudos@ibtec.org.br
CNPJ 87.190.161/0001-73
Inscrição Estadual: 086/0422534

Rua Araxá, 750
Bairro Ideal
93334-000
Novo Hamburgo
Rio Grande do Sul, Brasil

TEST REPORT SR 0645/22

Novo Hamburgo, March 07th, 2022.

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.

Phone +55 51 3553.1000
www.ibtec.org.br
laudos@ibtec.org.br
CNPJ 87.190.161/0001-73
Inscrição Estadual: 086/0422534

Rua Araxá, 750
Bairro Ideal
93334-000
Novo Hamburgo
Rio Grande do Sul, Brasil

TEST REPORT SR 0645/22

Dienifer C. S. Krug

Technical Analyst
Dienifer C. Scheeren Krug - Chemical technician
CRQ 05409288 - 5ª Region

To verify the authenticity of this document, download a QR code reader. Open the app and point the camera at the picture or check the address:

Digital signature: This report receives digital signature with digital certification according with Medida Provisória N° 2200-2 de 28/08/2001. When viewing the file, search the following icon on the pdf tools



toolbar. 

www.ibtec.org.br/areacliente/laudo/4187604223521407032022_ibtec_-_Assinado.pdf

Jaqueline Roese

Technical Analyst
Jaqueline Roese - Chemical technician
CRQ 05409456 - 5ª Region

Letícia S. Moser

Technical Analyst
Letícia Isabela Moser - Chemical technician
CRQ 054010382 - 5ª Region

Janiela C. Klein Gamarra

Test Supervisor
Janiela Cristina Klein Gamarra - Industrial Chemist
CRQ 05203543 - 5ª Region

Note: The results presented in this document are valid only to the tested samples and may not be reproduced without the laboratory authorization. Authorization will only be given for the total reproduction of this document.